



EDGT PRIZMA

TECHNICAL DATA SHEET

Product code

H49

Description

Hardener P.U White.

Main uses

Catalyst for Pigmented High Solids Matt P.U Topcoats .

Technical data

Specific Gravity, kg/l :1.01
Viscosity (Ford cup 4) @ 25 :11.6 sec
Solids by Weight H49 as Supplied :32%

Mixing ratio

By Volume :50%
For Pigmented Polyurethane Matt Topcoats
LU4910-20-30-50-70 LU500 series

Technical information

High Hardness and Flexibility
Medium Fast Drying.
Yellowing Resistant

N.B

Keep away from Water and Damp Areas

Storage stability

12 months; in closed container at 30°C max and protect from moisture.