



## EDGT PRIZMA

### TECHNICAL DATA SHEET

<b><u>Product code:</u></b>	<b>LU12</b>
<b><u>Description:</u></b>	<b>Clear polyurethane matt top coat</b>
<b><u>Properties:</u></b>	High quality topcoats suited for all kinds of matt finishes.
<b><u>Main uses:</u></b>	Clear polyurethane topcoats, suitable for open and closed grain system, for flat and assembled furniture, chairs.
<b><u>Technical data:</u></b>	Specific gravity, kg/l : 0.98 Viscosity ford cup 4 @ 25 : 27 sec Solid by weights supplied : 43% Solid by weights hardener H20 A : 32 % Solid by weight after catalysis : 38% Pot life, at 20 C : 3 hours
<b><u>Mixing ratio:</u></b>	LU12 : 100 parts by weight or volume H20A : 50 parts by weight or volume PU thinner : 15 parts by weight or volume
<b><u>Technical information:</u></b>	Application system : by spray gun Application viscosity : 15(+ or-2) sec Number of coats Dust :1 free time : 10 to 15 min Dry for stacking : 18 hours (at 25°)
<b><u>Available sheens:</u></b>	On 60° angle  LU 12 :50% gloss (±2)
<b><u>Storage stability:</u></b>	12 months; in closed container at 30 °C max and protect from moisture.