



## EDGT PRIZMA

### TECHNICAL DATA SHEET

<b><u>Product code</u></b>	<b>LU 4950</b>												
<b><u>Description</u></b>	<b>White Polyurethane Matt Finish.</b>												
<b><u>Properties</u></b>	Very High covering power, high-level of hardness and flexibility, Uniform Matting and a soft touch												
<b><u>Main uses</u></b>	Suitable for flat panels and assembled furniture.												
<b><u>Technical data</u></b>	Specific gravity, kg/l :1.33 Viscosity @ 25 degrees Celsius : 75 > 80 KU Solid by weight supplied :65% Solid by weight hardener H 49 F :33% Solid by weight after catalysis :48% Pot life, at 25°C 3 hours												
<b><u>Mixing ratio</u></b>	<table><thead><tr><th></th><th>By weight</th><th>By volume</th></tr></thead><tbody><tr><td>LU 4950</td><td>:133</td><td>100</td></tr><tr><td>H 49</td><td>:50</td><td>50</td></tr><tr><td>S 102</td><td>:30</td><td>45</td></tr></tbody></table>		By weight	By volume	LU 4950	:133	100	H 49	:50	50	S 102	:30	45
	By weight	By volume											
LU 4950	:133	100											
H 49	:50	50											
S 102	:30	45											
<b><u>Technical information</u></b>	Application system By spray gun Application viscosity :15 sec Number of coats :1 or 2 Dust free time :15-20 min Dry for staking :48 hours (@25°C)												
<b><u>Available sheens</u></b>	On 60° angle LU 4950 :50% gloss (±5)												
<b><u>Storage stability</u></b>	12 months; in closed container at 30°C max and protect from moisture.												