



EDGT PRIZMA

TECHNICAL DATA SHEET

<u>Product code</u>	LU45
<u>Description</u>	White Polyurethane high gloss Topcoat.
<u>Properties</u>	Excellent coverage, brightness and gloss. Excellent flow and levelness.
<u>Main uses</u>	By spray gun on polyurethane or polyester primer.
<u>Technical data</u>	Specific gravity, kg/l :1.33 Viscosity @ 25 Krebs unit :74 KU Solid by weight as supplied :65% Solid by weight, hardener H10 :43% Solids by weight after catalysis :50.5% Pot live @ 25°C :3 hours
<u>Mixing ratio</u>	by volume By weight LU 45 :100 p :133 H 45 :50 p 50 PU thinner :25-40 p :20-35
<u>Technical data</u>	Application system :By spray gun Application viscosity :16 ± 1 sec Number of coats :1 or 2 Dust free time :20 to 30 min Dry for staking :36 hours Dry for polishing :36 hours (@25°C)
<u>Storage stability</u>	12 months; in closed container at 30 °C max and protect from moisture.